

Bamtac BTR630A

Бамбуковое волокно

Styrene Butadiene Styrene Block Copolymer

Ningbo Bamtac New Material Col, Ltd.

Описание материалов:

BTR630A, which includes the compounds of SBS resin with bamboo fiber, maintains the antibiosis and deodorization features of bamboo. This products have been successfully applied in handle coating and it also can be applied in shoes material and toys, like bassinet wheel, cushion and ect....

Главная Информация			
Наполнитель/армирование	Бамбуковое волокно		
Используется	Обувь		
	Игрушки		
Физический	Номинальное значение	Единица измерения	Метод испытания
Плотность	0.980 to 1.07	g/cm ³	ISO 1183
Массовый расход расплава (MFR) (200°C/5.0 kg)	20 to 25	g/10 min	ISO 1133
Усадка	0.50 to 1.0	%	
Твердость	Номинальное значение	Единица измерения	Метод испытания
Твердость по суше (Shore A)	65 to 70		
Механические	Номинальное значение	Единица измерения	Метод испытания
Модуль растяжения	> 20.0	MPa	ISO 527-2
Tensile Stress	> 2.00	MPa	ISO 527-2
Растяжимое напряжение (Break)	> 500	%	ISO 527-2

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай



WeChat