

## Paraclean® 28L35

Acrylonitrile Butadiene Rubber

INSA

### Описание материалов:

Description:

"Clean" Low Volatility nbr for injection molding.

Fast Curing,

Excellent low temperature flexibility with moderate oil resistance.

Low water absorption.

Low corrosion.

Cold polymerized.

Non staining stabilizer.

Applications:

Injection molded products.

O-rings, seals, gaskets, grommets, and diaphragms.

Hose and tubes requiring low temperature flexibility.

### Главная Информация

Характеристики	Быстрое лечение
	Хорошая технологичность
	Гибкость при низкой температуре
	Низкое поглощение воды
	Устойчивый к пятнам
Используется	Диафрагмы
	Прокладки
	Прокладки
	Шланг
	Уплотнения
	Трубка
Метод обработки	Литье под давлением

Физический	Номинальное значение	Единица измерения	Метод испытания
Удельный вес	0.970	g/cm <sup>3</sup>	ASTM D297
Вязкость Mooney (ML 1+4, 100°C)	28 to 42	MU	ASTM D1646
Содержание АСN-Скрепленный	26.5 to 29.5	wt%	Internal Method
Содержание золы	< 0.8	wt%	ASTM D5667
Летучее вещество	< 1.0	wt%	ASTM D5668

\* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

## Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

