

Tecnoflon® FOR 7380K

Fluoroelastomer

Solvay Specialty Polymers

Описание материалов:

TECNOFLON® FOR 7380K is a medium viscosity cure incorporated fluoroelastomer terpolymer (FKM) with 68 % fluorine content. Tecnoflon® FOR 7380K is designed to improve bonding in any application requiring adhesion to metal. In shaft seals or valve stem seals production, Tecnoflon® FOR 7380K greatly reduces the reject rate due to adhesion and molding problems. Tecnoflon® FOR 7380K contains a new curing system and proprietary special processing aid, providing superior processability for fast cycles and scorch safety.

Some of the basic properties of Tecnoflon® FOR 7380K are:

Very good flow

Superior rubber-to-metal bond

Lack of mould fouling

Excellent hot tear resistance

Tecnoflon® FOR 7380K can be used for compression, injection and transfer molding of shaft seals, valve stem seals, O-rings, gaskets and seals. This material can be extruded into hoses or profiles and can be calendered to make sheet stocks or belting. Tecnoflon® FOR 7380K can be combined with the cure system and other typical fluoroelastomer compounding ingredients. Mixing can be accomplished with two-roll mills or internal mixers.

Главная Информация

Добавка	Обработка помощи
Характеристики	Bondability
	Цикл быстрого формования
	Хорошая адгезия
	Хороший поток
	Хороший выпуск пресс-формы
	Хорошая технологичность
	Хорошая прочность на разрыв
	Средняя вязкость
Терполимер	
Используется	Ремни/ремонт ремней
	Смешивание
	Прокладки
	Шланг
	Профили
	Уплотнения
	Лист
Клапаны/Детали Клапана	
Внешний вид	Кремowo-белый
Формы	Плита
Метод обработки	Каландрирование

Уплотнение
Прессформа сжатия
Экструзия
Литье под давлением
Литье из смолы

Физический	Номинальное значение	Единица измерения
Вязкость Mooney ¹ (ML 1+10, 121°C)	32	MU
Содержание фтора ²	68	%

NOTE

1. Raw polymer
2. Raw polymer

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

