

## SEQUEL® 1497 PUV NH533 BLK

Thermoplastic Polyolefin Elastomer

LyondellBasell Industries

### Описание материалов:

Sequel 1497 PUV NH533 BLK is a very high melt flow TPO with good stiffness and excellent cold temperature impact. It is typically used for easy flow and fast molding. It has low density that reduces part weight and improves paint adhesion and is formulated for fully painted exterior trim and fascia applications.

Главная Информация		
Используется	Забор для автомобильных дорожных ограждений Применение в автомобильной области Автомобильные внешние части	
Метод обработки	Литье под давлением	
Физический	Номинальное значение	Единица измерения
Плотность	0.940	g/cm <sup>3</sup>
Массовый расход расплава (MFR) (230°C/2.16 kg)	33	g/10 min
Механические	Номинальное значение	Единица измерения
Прочность на растяжение <sup>1</sup> (Yield, 23°C)	18.0	MPa
Флекторный модуль <sup>2</sup> (23°C)	1200	MPa
Воздействие	Номинальное значение	Единица измерения
Ударная прочность		
-30°C	5.0	kJ/m <sup>2</sup>
23°C	42	kJ/m <sup>2</sup>
NOTE		
1.	50 mm/min	
2.	2.0 mm/min	

\* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

### Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

