

Royalite R522

Acrylic (PMMA) + PVC

Spartech Plastics

Описание материалов:

ROYALITE® R522 is a fire rated proprietary thermoplastic sheet product that is engineered to meet the requirements of the FAR 25.853a flammability test.

R522 combines very high impact strength and stiffness with excellent formability. It has a high resistance to normal food and environmental stains and its cleanability with common cleaners is outstanding. Manufactured utilizing our proprietary cap sheet technology, R522 provides outstanding color and gloss control and superior grain retention after thermoforming.

APPLICATIONS:

The combination of toughness, durability, and fire retardancy makes Royalite® R522 the perfect choice for a wide variety of aircraft cabin applications. Its excellent chemical and abrasion resistance makes it suitable for all seating components, such as tray tables, end bays, and arm rests. The superior forming characteristics of R522 also make it a great material for the complex configurations of galley structures and lavatory interiors.

PROCESSING

You can process this rigid thermoplastic sheet on virtually all thermoforming equipment from high-volume, multi-station rotary machines to hand-operated presses. It is readily handformed for prototyping, and is suitable for use with aluminum and epoxy molds and fine-grain wood molds such as mahogany. Because Royalite® R522 is a PVC alloy, care must be taken in forming so as not to overheat the sheet. Stock temperatures of approximately 320-390°F are recommended for proper forming. As with any thermoplastic material, care should be taken to account for the coefficient of thermal expansion when considering design parameters. Please contact Spartech for data relating to your specific application and equipment. COLORS & TEXTURES:

Royalite® R522 sheet can be supplied in a variety of colors and over 24 different grain patterns to meet specific aesthetic requirements. This Royalite product is normally capped with calendered film, which provides exceptional color and gloss control, plus outstanding grain retention after forming. FINISHING:

You can machine, saw, drill, rout and grind this rigid sheet with conventional plastics fabricating equipment. It can be punched and die-cut, sanded and polished easily. So long as proper procedures are followed, you can join it to itself, or other materials, by adhesive bonding, ultrasonic welding, and by mechanical fasteners. Please contact Spartech for specific recommendations.

CHEMICAL & STAIN RESISTANCE, CLEANABILITY:

Royalite® R522 is resistant to a wide range of concentrated chemicals, and also exhibits very good stain resistance to common staining agents. Therefore, it is easily and safely cleaned with mild detergents or common cleansers. As with all plastics, extreme care should be taken when selecting a cleaning agent; some solutions may leave a residue or discolor the material. Mild soap and water are recommended; any other solution should be used with extreme caution as it may cause discoloration or degrade the material. Contact Spartech for suggested guidelines.

AVAILABILITY:

Royalite® R522 is available in various custom colors, grain textures, gauges, and blank sizes subject to normal product scheduling. Maximum width available is 60". The available gauge range is 0.031" - 0.375". Some restrictions apply to widths greater than 55".

Главная Информация

Характеристики Ультра высокая ударопрочность

Сверхвысокая прочность

Жесткий, высокий

Высокая прочность на растяжение

Сопротивление пятнам

Распылитель

Обрабатываемый

Очищаемый

Хорошая окраска

Хорошая стойкость к истиранию

Хорошая химическая стойкость



	Теплостойкость, высокая		
	Долговечность		
	Огнестойкий		
Используется	Интерьер самолета		
	Кронштейн Лоток		
	Сиденье		
Рейтинг агентства	Далеко 25-25853А		
	· ·		
Внешний вид	Доступные цвета		
Формы	Частицы		
Метод обработки	Термоформовка		
Физический	Номинальное значение	Единица измерения	Метод испытания
Удельный вес ¹	1.27 - 1.30	g/cm ³	ASTM D792
Формовочная усадка-Поток (3.18 mm)	0.50 - 0.70	%	ASTM D955
Твердость	Номинальное значение	Единица измерения	Метод испытания
Твердость Роквелла (R-Scale, 3.18 mm)	100		ASTM D785
Механические	Номинальное значение	Единица измерения	Метод испытания
Прочность на растяжение-Поток (Yield, 3.18 mm)	40.7	МРа	ASTM D638
Флекторный модуль (3.18 mm)	2480	MPa	ASTM D790
Flexural Strength (3.18 mm)	66.2	MPa	ASTM D790
Воздействие	Номинальное значение	Единица измерения	Метод испытания
Зубчатый изод Impact (23°C, 3.18 mm)	800	J/m	ASTM D256
Ударное падение Dart (23°C, 3.18 mm)	36.2	J	ASTM D5420
Тепловой	Номинальное значение	Единица измерения	Метод испытания
Температура отклонения при нагрузке (1.8 MPa, Annealed, 3.18 mm)	75.0	°C	ASTM D648
Воспламеняемость	Номинальное значение		
	Номинальное значение Passes		
Воспламеняемость Воспламеняемость ² (787.4 µm) Thermoforming Molding Temperature		°C	
Воспламеняемость ² (787.4 µm) Thermoforming Molding Temperature	Passes	°C	
	Passes	°C	

^{*} Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами



Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

