

Tecnoflon® P 757

Fluoroelastomer

Solvay Specialty Polymers

Описание материалов:

TECNOFLON® P 757 is a medium viscosity, medium fluorine (67%), peroxide curable fluoroelastomer. Tecnoflon® P 757 exhibits superior resistance to a wide variety of chemicals, coupled with excellent processability, optimum compression set and good flexibility at low temperatures. Tecnoflon® P 757 can be cross-linked using organic peroxides in conjunction with a coagent.

Some of the basic properties of TECNOFLON® P 757 are:

Low post cure

Superior mold flow

Lack of mold fouling

Excellent mold release

Good chemical resistance

Good stress relaxation

Good metal bonding

Good low temperature performance

Tecnoflon® P 757 can be used for compression, injection and transfer molding of shaft seals, valve seals, O-rings, gaskets or any item requiring superior chemical resistance.

Tecnoflon® P 757 can be combined with the cure system and other typical fluoroelastomer compounding ingredients. Mixing can be accomplished with two-roll mills or internal mixers. This material can be extruded into hoses or profiles and can be calendered to make sheet stocks or belting.

Finished goods may be produced by a variety of rubber processing methods.

Главная Информация

Характеристики

Bondability

Crosslinkable

Хорошая химическая стойкость

Хороший поток

Хороший выпуск пресс-формы

Хорошая технологичность

Комплект низкого сжатия

Гибкость при низкой температуре

Средняя вязкость

Используется

Ремни/ремонт ремней

Смешивание

Прокладки

Шланг

Применение при низкой температуре

Металлическое соединение

Профили

Уплотнения

Лист

Клапаны/Детали Клапана

Внешний вид	Полупрозрачный
Формы	Плита
Метод обработки	Каландрирование Уплотнение Прессформа сжатия Экструзия Литье под давлением Литье из смолы

Физический	Номинальное значение	Единица измерения
Вязкость Mooney ¹ (ML 1+10, 121°C)	44	MU
Содержание фтора ²	67	%

NOTE

1. Raw polymer
2. Raw polymer

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

