

Kuraray Poval® PVA 205MB

Polyvinyl Alcohol

Kuraray Co., Ltd.

Описание материалов:

Partially hydrolysed grade - anti-foaming/defoaming grade

Mowiol® and Kuraray Poval® are the trade name of the polyvinyl alcohols marketed by Kuraray. These are manufactured from polyvinyl acetate by alcoholysis using a continuous process. By varying the degree of polymerization of the polyvinyl acetate and its degree of hydrolysis (saponification), a number of different grades can be supplied. Our PVOH types are offered in a high standard purity showing especially "low ash and VOC contents". Modification of emulsion adhesives, production of paper adhesives and remoistenable adhesives. Protective colloid in emulsion polymerisation and raw material for the production of sizes and textile finishes. Binder in the surface finishing of paper. Also for regulating the processing characteristics of all types of coatings.

| Главная Информация | | | |
|-----------------------------------|---|-------------------|-----------------|
| Характеристики | Барьерная смола Биоразлагаемый Хорошая адгезия Хорошая цветность Водорастворимый | | |
| Используется | Клеи Связыватель Строительные материалы Нанесение покрытия Пленка Покрытия из фольги Бумажные Покрытия Текстильные изделия | | |
| Формы | Гранулы | | |
| Физический | Номинальное значение | Единица измерения | Метод испытания |
| Вязкость раствора ¹ | 5 | mPa·s | JIS K6726 |
| Содержание золы ² | < 0.40 | % | |
| pH ³ | 4.5 to 7.0 | | |
| Летучее вещество | < 5.0 | % | |
| Degree of Hydrolysis ⁴ | 87 to 89 | % | |
| Добыча метанола | < 3.0 | % | |

NOTE

1.

4 % aqueous solution at 20 °C,
determined by Brookfield
synchronised-motor rotary-type
viscometer

- | | |
|----|---------------------------------|
| 2. | Calculated as Na2O |
| 3. | 4 % solution in distilled water |
| 4. | Saponification |

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

