

Lushan PR296B

Polypropylene

Guangzhou Lushan New Materials Co., Ltd

Описание материалов:

Adhesive Resin for Aluminium plastic Composite Pipe

Adhesive resin Lushan series for aluminum-plastic composite pipe is maleic grafted polyethylene used for PE-AL- PE, PEX-AL- PEX and PERT-AL- PERT composite pipes. Lushan adhesive resin could provides innovative solutions for plumbing and heating pipe systems including applications of domestic water piping, under-floor heating, radiator connections and wall, cooling and heating installations, district heating and industrial piping, etc. PPR pipe adhesive resin Lushan series is maleic grafted polypropylene used for PPR piping system. As a breakthrough of PP grafted materials, Lushan makes its adhesive resin to be possible to combine the advantages of materials and polymers in the multi-layer aluminium plastic composite structures. The high mechanical and thermal cycle resistance of Lushan adhesive resin provide an excellent bonding effect over a wide temperature range.

| Главная Информация | | | |
|---|----------------------|-------------------|-----------------|
| Характеристики | Bondability | | |
| Используется | Клеи | | |
| | Трубопроводы | | |
| | Детали сантехники | | |
| Формы | Гранулы | | |
| Метод обработки | Кокэкструзия | | |
| Физический | Номинальное значение | Единица измерения | Метод испытания |
| Плотность | 0.900 | g/cm ³ | ASTM D1505 |
| Массовый расход расплава (MFR) (230°C/2.16 kg) | 5.0 | g/10 min | ASTM D1238 |
| Механические | Номинальное значение | Единица измерения | Метод испытания |
| Удлинение при растяжении (Break) | 300 | % | ASTM D638 |
| Тепловой | Номинальное значение | Единица измерения | Метод испытания |
| Викат Температура размягчения | 100 | °C | ASTM D1525 |
| Пиковая температура плавления | 155 | °C | ASTM D2117 |

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

