

Teflon® FEP CJ 95

Perfluoroethylene Propylene Copolymer

DuPont Fluoropolymers

Описание материалов:

For inventory control purposes product name may be followed by an X.

Products labeled FEP CJ 95 and FEP CJ 95 X are equivalent and all information in this document is applicable to both.

Typical Application

Insulation and jacket for Wire and Cable, in applications demanding a high degree of stress crack resistance. Tubes and piping for general and chemical process industry.

DuPont Teflon ® FEP CJ 95 is a melt-processible copolymer of tetrafluoroethylene and hexafluoropropylene without additives that meets the requirements of ASTM D 2116 type I.

It offers the excellent combination of properties characteristic of Teflon ® fluoropolymer resins: non-ageing characteristics, chemical inertness, exceptional dielectric properties, low flammability, heat resistance, toughness and flexibility, low coefficient of friction, non-stick characteristics, negligible moisture absorption and excellent weather resistance. As an intermediate molecular weight resin Teflon ® FEP CJ 95 offers higher processing speeds than many FEP grades with similar high level of stress crack resistance.

Stress crack resistance is an important element in establishing end-use performance. Extensive testing of wire and cable constructions is required for definitive performance evaluation. Experience shows that the MIT folding endurance or flex life test, performed on a thin film of resin, has established a good correlation with extensive cable testing. The higher the MIT

flex life, the higher the stress-crack resistance of the resin. MIT test results should be viewed as a guide to comparative performance of the various grades of resin. We recommend that for applications involving repeated thermal and flex cycling, specific tests on the final cable always should be undertaken. See also DuPont's bulletin "Grade selector for Wire and Cable applications".

Главная Информация

| | |
|-------------------|--|
| UL YellowCard | E54681-557110 |
| Характеристики | <p>Приемлемый пищевой контакт</p> <p>Хорошая химическая стойкость</p> <p>Хорошая гибкость</p> <p>Хорошая прочность</p> <p>Хорошая устойчивость к погоде</p> <p>Высокий уровень ЭСКП (устойчивость к стрессу)</p> <p>Высокая термостойкость</p> <p>Низкое трение</p> <p>Низкое поглощение влаги</p> |
| Используется | <p>Кабельный кожух</p> <p>Изоляция</p> <p>Применение проводов и кабелей</p> |
| Рейтинг агентства | <p>Стандарт ASTM D 2116 тип 1</p> <p>EC 10/2011</p> <p>Управление по санитарному надзору за качеством пищевых продуктов и медикаментов 21 CFR 177,1550</p> |
| Формы | Гранулы |

| | |
|-----------------|--|
| Метод обработки | Выдувное формование Прессформа сжатия Экструзия Литье под давлением |
|-----------------|--|

| Физический | Номинальное значение | Единица измерения | Метод испытания |
|--|----------------------|-------------------|------------------------|
| Удельный вес | 2.13 | g/cm ³ | ASTM D792, ISO 1183 |
| Массовый расход расплава (MFR) (372°C/5.0 kg) | 5.0 | g/10 min | ASTM D2116, ISO 12086 |
| Поглощение воды (24 hr) | < 0.010 | % | ASTM D570 |
| Твердость | Номинальное значение | Единица измерения | Метод испытания |
| Твердость дюрометра (Shore D) | 56 | | ASTM D2240, ISO 868 |
| Механические | Номинальное значение | Единица измерения | Метод испытания |
| Прочность на растяжение (Yield, 23°C) | 28.0 | MPa | ASTM D638, ISO 12086 |
| Удлинение при растяжении (Break, 23°C) | 330 | % | ASTM D638, ISO 12086 |
| Воздействие | Номинальное значение | Единица измерения | Метод испытания |
| Зубчатый изод Impact (23°C) | No Break | | ASTM D256, ISO 180 |
| Тепловой | Номинальное значение | Единица измерения | |
| Температура непрерывного использования ¹ | 205 | °C | |
| Температура плавления ² | 260 | °C | |
| Электрический | Номинальное значение | Единица измерения | Метод испытания |
| Диэлектрическая прочность | | | |
| 0.250 mm ³ | > 95 | kV/mm | ASTM D149 |
| 0.250 mm | > 95 | kV/mm | IEC 60243-1 |
| Диэлектрическая постоянная | | | ASTM D150, IEC 60250 |
| 1 kHz | 2.03 | | |
| 1.00 GHz | 2.03 | | |
| Коэффициент рассеивания | | | ASTM D150, IEC 60250 |
| 1 kHz | 5.0E-5 | | |
| 1.00 GHz | 8.0E-4 | | |
| Воспламеняемость | Номинальное значение | Единица измерения | Метод испытания |
| Огнестойкость ⁴ | V-0 | | UL 94 |
| Индекс кислорода | > 95 | % | ASTM D2863, ISO 4589-2 |
| Дополнительная информация | Номинальное значение | Единица измерения | Метод испытания |
| Критическая частота сдвига (372 °C) | 20.0 | sec^-1 | Internal Method |
| Направляющий диапазон DDR | | | |
| for cable extrusion | 20.0 to 120 | | |
| for tubing extrusion | 3.00 to 8.00 | | |

MIT Складной

Выносливость-Пленка(200,0 мкм)

4.0E+4

Cycles

ASTM D2176

NOTE

The continuous service temperature is based on accelerated heat-aging tests, and represents the temperature at which tensile strength and ultimate elongation retains 50% of the original values, after 20 000 h thermal aging. When considering the use of Teflon ® FEP at elevated temperatures especially in combination with mechanical, electrical or chemical exposure, preliminary testing should be done

1. to verify suitability.

2. ASTM D4591 / D3418

3. Method A (Short-Time)

- These results are based on laboratory tests, under controlled conditions, and do not reflect performance under actual fire conditions.- Current rating is a typical theoretical value

4.

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

