

Sumiliteresin® PR-1305 I

Карбонат кальция 11%

Phenolic

SBHPP

Описание материалов:

SUMILITERESIN® PR-1305 I is a straight novolak type powder with filler content. It is generally apply for Felt.

Characteristics

SUMILITERESIN® PR-1305 I is powder phenolic resin including hexamine and filler CaCO₃.

SUMILITERESIN® PR-1305 I has high molecule weight and filler about 11%. By using this type, resin will not be easy to caking and sticking, good for molding process, hardness & strenght properties in application.

SUMILITERESIN® PR-1305 I is high reactive type, process time can be reduced.

Главная Информация		
Наполнитель/армирование	Перламутровый наполнитель, 11% Упаковка по весу	
Характеристики	Высокорреактивная	
	Высокая Молекулярная масса	
	Обрабатываемость, хорошая	
	Хорошая прочность	
Внешний вид	Белый	
	Желтый	
Формы	Порошок	
Физический	Номинальное значение	Единица измерения
Длина потока (125°C)	1.80 - 3.20	cm
Анализ сита-106µm		%
Гекса	7.5 - 8.5	%
Uncured Properties	Номинальное значение	Единица измерения
Gel Time (150°C)	0.92 - 1.4	min

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

