

Escorene™ Ultra FL 00328

Ethylene Vinyl Acetate Copolymer Resin

ExxonMobil Chemical

Описание материалов:

FL 00328 is a copolymer of ethylene and vinyl acetate with low crystal point. When the processing temperature is higher than 220 C (428 °F) in processing conditions, resin degradation may be caused. The machine should be thoroughly cleaned with low density polyethylene or suitable detergent before stopping.

Главная Информация			
Физический	Номинальное значение	Единица измерения	Метод испытания
Содержание винилацетата	27.0	wt%	ExxonMobil Method
Твердость	Номинальное значение	Единица измерения	Метод испытания
Твердость дюрометра (Shore A, 15 sec)	80		ASTM D2240
Механические	Номинальное значение	Единица измерения	Метод испытания
Модуль растяжения ¹	19.0	MPa	ASTM D638
Удлинение при растяжении ² (Break)	> 100	%	ASTM D638
Тепловой	Номинальное значение	Единица измерения	Метод испытания
Викат Температура размягчения	44.0	°C	ASTM D1525

Юридическое заявление

此产品符合(符合: FDA, EU, HPFB), 符合相关标准。 符合相关标准, 符合相关标准。

NOTE

1.	5.0 mm/min
2.	500 mm/min

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519
 Мобильный телефон: +86-13424755533
 Email: sales@su-jiao.com
 Адрес: Господин Чжао
 Район Фэнсянь, Шанхай, Китай

