

## MARPOL® PET IV 84 CB

Polyethylene Terephthalate

Marco Polo International, Inc.

### Описание материалов:

Features:

Good process ability

Excellent clarity/gloss

Very Good mechanicals

It is typically used for:

Carbonated drinks.

Agro chemicals

APET sheet and PET strapping

Certifications:

PET MarPol IV 84 CB resin is considered safe for food-packaging applications based on compliance with FDA regulation 21 CFR Section 177.1630 & other similar food contact safety regulations.

Главная Информация	
Характеристики	Приемлемый пищевой контакт Хорошая технологичность Высокая четкость Глянцевый
Используется	Применение в сельском хозяйстве Бутылки Лист Обвязка
Рейтинг агентства	Управление по санитарному надзору за качеством пищевых продуктов и медикаментов 21 CFR 177,1630

Физический	Номинальное значение	Единица измерения	Метод испытания
Ацетальдегид	1.0	ppm	Internal Method
Цвет b-CIE	-3.00 to 0.00		Internal Method
Crystallinity	50	%	Internal Method
Внутренняя вязкость	0.84	dl/g	Internal Method
Чипы/грамм	72.0		Internal Method
Штрафы	100	ppm	Internal Method

\* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

**Susheng Import & Export Trading Co.,Ltd.**

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

