

## S.O.E.™ S1606

Styrene Butadiene Block Copolymer

AKelastomers

### Описание материалов:

Asahi Kasei S.O.E.™ S1606 is a special SEBS with low resilience. It can be used as a modifier to improve scratch resistance and abrasion resistance of TPE compounds. It also offers good compatibility between PS and polyphenylene ether (PPE). It is also used as a modifier of COP and COC.

Главная Информация			
Характеристики	Хорошая стойкость к истиранию Устойчивость к царапинам		
Формы	Частицы		
Физический	Номинальное значение	Единица измерения	Метод испытания
Плотность	0.980	g/cm <sup>3</sup>	ISO 1183
Массовый расход расплава (MFR) (230°C/2.16 kg)	4.0	g/10 min	ISO 1133
Твердость	Номинальное значение	Единица измерения	Метод испытания
Твердость дюрометра (Shore A)	67		ISO 868
Эластомеры	Номинальное значение	Единица измерения	Метод испытания
Tensile Stress <sup>1</sup> (300% Strain)	3.60	MPa	ISO 37
Tensile Stress <sup>2</sup> (Yield)	20.0	MPa	ISO 37
Удлинение при растяжении <sup>3</sup> (Break)	490	%	ISO 37
NOTE			
1.	500 mm/min		
2.	Type 1A, 500 mm/min		
3.	Type 1A, 500mm/min		

\* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

### Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

