

ELASTOSIL® R 401/60

Silicone

Wacker Chemie AG

Описание материалов:

Silicone Rubber, HTV

Extruded parts; tap water and wastewater contact, Automotive & Transportation

Hoses, Automotive, Automotive & Transportation

Spark Plugs Boots, Automotive & Transportation

Exhaust-Pipe Suspensions, Automotive & Transportation

Vibration Dampers, Automotive & Transportation

Molded Seals, Plastics and Rubber Processing

Membranes, Automotive & Transportation

Ignition and Battery Cables, Cable Industry

Ignition and Battery Cables, Automotive & Transportation

Extrudates, Automotive, Plastics and Rubber Processing

Extrudates, food contact, Plastics and Rubber Processing

Extruded parts; tap water and wastewater contact, Plastics and Rubber Processing

Extrudates, Technical, Plastics and Rubber Processing

Molded Parts, Automotive, Plastics and Rubber Processing

Molded Parts, Food Contact, Plastics and Rubber Processing

Molded Parts, Technical, Plastics and Rubber Processing

Molded parts; tap water and wastewater contact, Plastics and Rubber Processing

Sealant Profiles, Construction

Главная Информация

UL YellowCard	E75704-101818639
Характеристики	Приемлемый пищевой контакт Общее назначение
Используется	Автомобильные Приложения Уплотнение Прокладки Применение питьевой воды Профили Уплотнения Клапаны/Детали Клапана Применение проводов и кабелей
Метод обработки	Каландрирование Прессформа сжатия Экструзия Пресс-форма Экструзионный профиль Провод и кабель экструзии

Uncured Properties	Номинальное значение	Единица измерения	Метод испытания
Цвет	Clear/Transparent		
Плотность	1.15	g/cm ³	ISO 1183
Cured Properties	Номинальное значение	Единица измерения	Метод испытания
Твердость по суше (Shore A)	61		DIN 53505
Прочность на растяжение	11.0	MPa	DIN 53504
Удлинение при разрыве	440	%	DIN 53504
Комплект сжатия	31	%	DIN ISO 815-B
Tear Strength	24.0	kN/m	ASTM D624B
Восстановленная устойчивость	57	%	DIN 53512

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай



WeChat