

MACOMASS PP MM-PP Reg

Polypropylene

MACOMASS Verkaufs AG

Описание материалов:

Regranulates are created by mechanically/physically processing sorted thermoplastic polymers. They are broken down, washed, dried, melted and reformed into granulates, which are then called regranulates.

Regranulates are used in plastics processing companies as a raw material. Depending on the quality and taking into account the desired properties of the product, regranulates can be used by themselves or in combination with new goods.

Главная Информация		
Переработанное содержание	Да	
Формы	Частицы, после переработки	
Физический	Номинальное значение	Единица измерения
Плотность	0.910 - 0.950	g/cm ³
Массовый расход расплава (MFR) (230°C/2.16 kg)	6.0 - 12	g/10 min
Механические	Номинальное значение	Единица измерения
Tensile Stress	> 20.0	MPa
Растяжимое напряжение (Break)	> 120	%
Воздействие	Номинальное значение	Единица измерения
Charpy Unnotched Impact Strength (23°C)	> 40	kJ/m ²

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай



WeChat