Escorene™ Ultra LD 768.MJ Molding

Ethylene Vinyl Acetate Copolymer Resin

ExxonMobil Chemical

Описание материалов:

Escorene Ultra LD 768.MJ is a high viscosity copolymer containing 26.2% vinyl acetate, which is suitable for making soft blow molded or extruded articles with excellent low temperature toughness. It can also be used as polymer modifier for manufacturing special compound granulation.

Главная Информация			
Добавка	Стабилизатор тепла		
Физический	**Номинальное значение**	**Единица измерения**	**Метод испытания**
Массовый расход расплава (MFR) (190°C/2.16 kg)	2.3	g/10 min	ASTM D1238
Содержание винилацетата	26.2	wt%	ExxonMobil Method
Твердость	**Номинальное значение**	**Единица измерения**	**Метод испытания**
Твердость дюрометра			ASTM D2240
Shaw A, 15 seconds	75		ASTM D2240
Shaw D, 15 seconds	28		ASTM D2240
Механические	**Номинальное значение**	**Единица измерения**	**Метод испытания**
Прочность на растяжение (Break)	9.45	MPa	ASTM D638
Удлинение при растяжении (Break)	> 800	%	ASTM D638
Флекторный модуль-1% Secant	31.0	MPa	ASTM D790
Воздействие	**Номинальное значение**	**Единица измерения**	**Метод испытания**
Ударное устройство для дротиков			ASTM D3763
-40°C	31.2	J	ASTM D3763
23°C	21.7	J	ASTM D3763
Тепловой	**Номинальное значение**	**Единица измерения**	**Метод испытания**
Викат Температура размягчения	49.0	°C	ASTM D1525

Юридическое заявление

□□□□□□□□□□□□□,□□□□□□□□□□□□□

Район Фэнсянь, Шанхай, Китай

WeChat