

## Prime Biogreen 650

Biodegradable Polymers

Primex Plastics Corporation

### Описание материалов:

Primex Corporation, along with our subsidiaries, are committed to sustainable practices that are ethical, responsible, and create value for customers, employees, and future generations.

Biodegradable/ Compostable Material

FDA status to be determined.

Flammability to be determined.

Главная Информация			
Характеристики	Биоразлагаемый Compostable		
Рейтинг агентства	ASTM D 6400		
Физический	Номинальное значение	Единица измерения	Метод испытания
Удельный вес	1.25	g/cm <sup>3</sup>	ASTM D792
Массовый расход расплава (MFR) (190°C/5.0 kg)	37	g/10 min	ASTM D1238
Механические	Номинальное значение	Единица измерения	Метод испытания
Прочность на растяжение			ASTM D638
Yield	51.0	MPa	
Break	31.0	MPa	
Удлинение при растяжении (Break)	9.0	%	ASTM D638
Тепловой	Номинальное значение	Единица измерения	Метод испытания
Температура отклонения при нагрузке (0.45 MPa, Unannealed)	52.8	°C	ASTM D648
Викат Температура размягчения	63.3	°C	ASTM D1525

\* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

### Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

