

ELASTOSIL® RT 675 A/B

Silicone

Wacker Chemie AG

Описание материалов:

Silicone Rubber, RTV-2

Thermally Conductive Rollers, Plastics and Rubber Processing

Thermally Conductive Rollers, Printing Industry

Potting Compound, Electronics

all-round potting compounds, Lighting

all-round potting compounds, Electrical Industry

all-round potting compounds, Automotive & Transportation

Potting Compound, Automotive & Transportation

Главная Информация	
Используется	Электрическое/электронное применение
Метод обработки	Инкапсулирование
	Полировка

Uncured Properties	Номинальное значение	Единица измерения	Метод испытания
Цвет	Brown		
Плотность	2.30	g/cm ³	ISO 2781
Вязкость	50	Pa·s	ISO 3219
Срок службы горшка	150	min	

Cured Properties	Номинальное значение	Единица измерения	Метод испытания
Твердость по суше (Shore A)	80		ISO 868
Прочность на растяжение	2.00	MPa	ISO 37
Удлинение при разрыве	20	%	ISO 37
Относительная проницаемость	5.00		IEC 60250
Сопrotивление громкости	1.0E+15	ohms-cm	IEC 60093

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

