

Kazan HDPE PEBO-285D

High Density Polyethylene

Kazanorgsintez Joint Stock Company

Описание материалов:

HDPE FILM GRADES 273-285, PE8D-2B5, 293-2B5D, PEBO-285D

GOST / TU: TU 2243-127-00203335-2000

Composition of 293-285D, PE80B-285D grades includes processing aids. Processing aid allows extruding polyethylene throughout narrower die head and avoiding carbon deposit while haul-off, that means to make a thinner film with good mechanical properties. According to the experience of end users of such products it is possible to make high-quality extrusion molded thin films (5 to 9 microns of film gauge) which can be used for food packaging. Production of thinner film decreases the cost of polyethylene to be processed in the cost of 1 m² of finished product. HDPE film grades have sanitary-and-epidemiologic authorization.

These grades are being manufactured based on 273,293, PE80B grades, have high molecular weight and wide MWD. The composition of products made on above polymers includes high-performance thermal stabilizers and processing aids which can improve processing. The grades are intended to process using extrusion method into high strength thin film and for other applications.

Главная Информация	
Добавка	Стабилизатор тепла Обработка помощи
Характеристики	Хорошая технологичность Высокая Молекулярная масса Широкое молекулярное распределение веса
Используется	Пленка
Формы	Гранулы
Метод обработки	Экструзия Экструзионная пленка

Физический	Номинальное значение	Единица измерения
Плотность	0.940 to 0.943	g/cm ³

Массовый расход расплава (MFR) (190°C/2.16 kg)	0.50 to 0.80	g/10 min
---	--------------	----------

Механические	Номинальное значение	Единица измерения
Tensile Stress		
Yield	> 16.0	MPa
Break	> 20.6	MPa
Растяжимое напряжение (Break)	> 700	%

Дополнительная информация	Номинальное значение	Единица измерения
Испарители	< 0.090	%

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

