

## Sumiliteresin® PR-50099 I

Phenolic

**SBHPP** 

## Описание материалов:

SUMILITERESIN® PR-50099 I is a standard straight novolak type powder form phenolic resin.

Characteristics

SUMILITERESIN® PR-50099 I is has hexamine content about 9% and high molecule weight and short flow.

For Friction Material: improve wear rate, high heat resistance and improve hardness.

For Bonded Abrasive: good moldability, preferable for depressed center and cutting wheel.

| Главная Информация    |   |                   |
|-----------------------|---|-------------------|
| Характеристики        | Высокая Молекулярная масса<br>Хорошая производительность формования |                   |
|                       |   |                   |
|                       |   |                   |
| Внешний вид           | Белый   |                   |
|                       | Желтый  |                   |
|                       |   |                   |
| Формы                 | Порошок   |                   |
| Физический            | Номинальное значение  | Единица измерения |
| Длина потока (125°C)  | 1.60 - 2.30   | cm                |
| Анализ сита-106µm     |   | %                 |
| Тепловой              | Номинальное значение  | Единица измерения |
| Температура плавления | 94.0 - 104  | °C                |
| Uncured Properties    | Номинальное значение  | Единица измерения |
| Gel Time (150°C)      | 1.5 - 2.2   | min               |

<sup>\*</sup> Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

## Свяжитесь с нами

## **Susheng Import & Export Trading Co.,Ltd.**

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com Адрес: Господин Чжао Район Фэнсянь, Шанхай, Китай



