

AXELERON™ CX A-0012 NT CPD

Nucleating Agent Masterbatch

The Dow Chemical Company

Описание материалов:

Dow AXELERON™CX A- 0012 NT is a masterbatch, which is used as a nucleating agent in gas injection processing. It is specially developed for easy mixing with DGDA-6944 NT or DGDB-6944 NT HDPE and DFDA-1253 NT LDPE. If used properly, the product will form a small, evenly distributed cell structure. The masterbatch is based on high-pressure LDPE resin and is added with a 10% heating chemical foaming agent. The use of this product should be 0.1% to 0.3% nucleating agent content, or 1-3% masterbatch content. Typical applications include CATV lead-in cables, models 59, 6, 7 and 11.

Главная Информация

Используется	Изоляция коаксиального кабеля
	Применение проводов и кабелей
	Главная партия
	Пена

Формы	Частицы
Метод обработки	Экструзия

Физический	Номинальное значение	Единица измерения	Метод испытания
Удельный вес	0.970	g/cm ³	ASTM D792
Массовый расход расплава (MFR) ¹ (190°C/2.16 kg)	2.0	g/10 min	ASTM D1238

Инструкции по экструзии

AXELERON™ CX A-0012 NT CPD is designed to be extruded with Dow's gas injection compounds AXELERON™ CX 6944 NT CPD HDPE and AXELERON™ CX 1253 NT CPD LDPE. It is normally added at 1-3% masterbatch concentration into a blend of 60-80% 6944 and 20-40% 1253. While the exact temperature profile required will depend upon the screw design and construction being made, the following extrusion temperature profile represents a good starting point:

Feed Zone: 285-300°F (140-150°C)

Transition Zone: 340-355°F (170-180°C)

Gas Injection Point: 340-375°F (170-190°C)

Metering Zone: 285-340°F (140-170°C); depends on diameter insulation

Crosshead and Die: 265-320°F (130-160°C); depends on diameter insulation

NOTE

1. Base Resin

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжоу

Район Фэнсянь, Шанхай, Китай



WeChat