

## Vinnolit® E 68 SA

Polyvinyl Chloride Homopolymer

Vinnolit GmbH & Co. KG

### Описание материалов:

Vinnolit E 68 SA is a fine-particle paste-making emulsion homopolymer, classified as a low to medium viscosity resin. Plastisols made with Vinnolit E 68 SA exhibit a nearly newtonian rheology.

Vinnolit E 68 SA is recommended for the production of chemically blown foams. Typical applications are for example artificial leather cloth, floorings, unsupported foams and foamed wall-coverings.

Главная Информация			
Используется	Напольное покрытие Пена		
Рейтинг агентства	EC 1907/2006 (REACH)		
Метод обработки	Пластик		
Физический	Номинальное значение	Единица измерения	Метод испытания
Видимая плотность	0.47	g/cm <sup>3</sup>	ISO 60
K-Value	68.0		ISO 1628-2
Viscosity Number (Reduced Viscosity)	116.0	ml/g	ISO 1628
Содержание эмульгатора	Medium		
Распределение размеров частиц <sup>1</sup>	< 3.0	%	ISO 4610
Летучее вещество	< 0.30	%	ISO 1269

### NOTE

1. retained on 0.063 mm screen

\* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

### Свяжитесь с нами

## Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

