

BR® 154

Еpoxy; Epoxide

Cytec Industries Inc.

Описание материалов:

BR® 154 is a modified epoxy, corrosion resistant primer developed for use with structural adhesive films demanding continuous mechanical performance at 350°F (177°C) with short time exposure up to 400°F (204°C). It is formulated to provide maximum environmental resistance and durability within the bond line.

Articles primed with BR 154 primer and cured have an indefinite shelf life. Primed details should be wrapped in Kraft paper (as protection from dust and dirt) and stored prior to adhesive bonding. Maintaining controlled conditions of 85°F (30°C) maximum temperature and 65% maximum humidity is recommended for extended storage life.

Главная Информация		
Характеристики	Прочный	
	Хорошая коррозионная стойкость	
	Хорошая термическая стабильность	
	Хорошая устойчивость к погоде	
	Высокая термостойкость	
	Устойчивость к окислению	
Используется	Склеивание	
	Детали конструкции	
Внешний вид	Желтый	
Метод обработки	Распыление	
Физический	Номинальное значение	Единица измерения
Удельный вес	0.871	g/cm ³

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

