

Andur 7501 DP

Polyurethane (Polyether, TDI)

Anderson Development Company

Описание материалов:

Andur 7501-DP is a polyether (PPG) based liquid, toluene diisocyanate terminated prepolymer. An elastomer with a hardness of 73 to 77 Shore D is obtained when this prepolymer is cured with Curene 442 [4,4'-methylene-bis (orthochloroaniline)]. Elastomers of lower hardness can be obtained by reaction with various polyols and their combination with Curene 442 and other diamines, or through the use of plasticizers.

| Главная Информация | | | |
|------------------------------------|----------------------|-------------------|-----------------|
| Термокомплект | Номинальное значение | Единица измерения | Метод испытания |
| Формы | Жидкость | | |
| Терморегулирующая вязкость (100°C) | 340 | сР | ASTM D2393 |
| Дополнительная информация | | | |
| NCO: 7.3 to 7.7% | | | |

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай



WeChat