

BP RPP 3005 GR BLK

30% стекловолокно

Polypropylene

Buckeye Polymers, Inc.

Описание материалов:

Product Information: Our Glass Reinforced product lines exhibit increased tensile strength, stiffness, and heat deflection. Highly optimized glass reinforced PP resins have successfully replaced engineering thermoplastics in numerous applications.

Features:

Good Flexural Strength

Chemically coupled

Главная Информация			
Наполнитель/армирование	Стекловолокно, 30% наполнитель по весу		
Характеристики	Химически Соединенные Хорошая прочность		
Используется	Инженерные приложения		
Внешний вид	Черный		
Физический	Номинальное значение	Единица измерения	Метод испытания
Удельный вес	1.11 to 1.15	g/cm ³	ASTM D792
Массовый расход расплава (MFR) (230°C/2.16 kg)	5.0 to 9.0	g/10 min	ASTM D1238
Содержание золы	28 to 32	%	ASTM D5630
Механические	Номинальное значение	Единица измерения	Метод испытания
Флекторный модуль (23°C)	> 4140	MPa	ASTM D790
Воздействие	Номинальное значение	Единица измерения	Метод испытания
Зубчатый изод Impact	> 64	J/m	ASTM D256

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

