

Accuply® 10

Thermoplastic

Accurate Plastics, Inc.

Описание материалов:

A multi use, matte finish, double sided film that will release from most synthetic resin systems: epoxies, phenolic, melamines, rubber, etc. For use in hand layup, from 0 pressure to high pressure applications (1500 PSI) and temperatures to 204 °C (400 °F).

Lamination of thermoset plastics, rubber and most synthetic resins. Highly versatile.

Главная Информация			
Используется	Пленка Ламинаты Многослойная пленка Лист		
Формы	Лист		
Физический	Номинальное значение	Единица измерения	Метод испытания
	0.0		
Формовочная усадка-Поток ¹ (190°C)	2.8	%	ASTM D955
Пленки	Номинальное значение	Единица измерения	Метод испытания
Прочность на растяжение			ASTM D882A
MD : Yield	96.5	MPa	
TD : Yield	96.5	MPa	
MD : Break	172	MPa	
TD : Break	207	MPa	
Удлинение при растяжении			ASTM D882A
MD : Break	90	%	
TD : Break	60	%	
Тепловой	Номинальное значение	Единица измерения	
Температура плавления	260	°C	
NOTE			
1.	Unrestrained 5 minutes		

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

