

Ultrason® E 2020 P SR micro

Polyethersulfone

BASF Corporation

Описание материалов:

Fine Polyethersulfone powder, e.g. for membrane applications, coatings and resin modification, containing min. 50% of OH-endgroups. The product has a typical particle size below 100 µm and is soluble in N-methyl-pyrrolidone (NMP) and N,N-Dimethylacetamide (DMAc). This grade is not suitable for thermoplastic moulding / extrusion.

Главная Информация			
Используется	Нанесение покрытия Мембраны Модификация пластмасс		
Рейтинг агентства	EC 1907/2006 (REACH)		
Соответствие RoHS	Соответствует RoHS		
Формы	Порошок		
Идентификатор смолы (ISO 1043)	Песу		
Физический	Номинальное значение	Единица измерения	Метод испытания
Видимая плотность	0.30	g/cm ³	ISO 60
Поглощение воды (Equilibrium, 23°C, 50% RH)	1.0	%	ISO 62
Номер вязкости ¹	59.0	cm ³ /g	ISO 307
Молекулярный вес-GPC в DMAc ²	55000	g/mol	

NOTE	
1.	in 0,01 g/ml Phenol/1,2, ortho-Dichlorbenzol, 1:1
2.	PMMA standard

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

