

OCTAL PET GP 02

Polyethylene Terephthalate

OCTAL Holding & Co.

Описание материалов:

OCTAL PET products are produced by the latest state-of-the-art technology involving 2R direct high I.V. process. This advanced technology ensures that the properties and quality of PET resin are superior with low crystallinity and low AA generation, thus making it the preferred product for a number of applications.

This is a food grade PET copolymer resin most suitable for a variety of applications including water, carbonated soft drinks, alcoholic beverages, hot fill, oil containers and pharmaceutical material packaging. This resin is developed and engineered to extend high dimensional strength and mechanical properties. The low degree of crystallinity and heat of fusion are some of the great advantages of OCTAL PET GP 02 to save energy and regeneration of acetaldehyde during the downstream processing. Its application is also suitable for heat set blow molding used for warm fill materials.

OCTAL PET GP 02 copolymer resin is considered safe for food packaging applications based on all compliance to USA FDA regulation CFR 21 section 177.1630, EU regulation 10/2011, EC Directive 94/62/EC and the CONEG regulations (USA/CANADA) for heavy metals contents.

Главная Информация			
Характеристики	Приемлемый пищевой контакт Хорошая стабильность размеров		
Используется	Бутылки Контейнеры Упаковка Фармацевтическая упаковка		
Рейтинг агентства	EC 10/2011 EC 94/62/EC Управление по санитарному надзору за качеством пищевых продуктов и медикаментов 21 CFR 177,1630		
Метод обработки	Выдвунное формование		
Физический	Номинальное значение	Единица измерения	Метод испытания
Ацетальдегид	< 1.0	ppm	Internal Method
Цвет b	< -0.500		Internal Method
Color L	> 84.0		Internal Method
Внутренняя вязкость	0.82 to 0.86	dl/g	Internal Method
Moisture Content ¹	< 0.10	wt%	Internal Method
Weight ²	1.4 to 1.8	g	Internal Method
Мелкие частицы	< 100	ppm	Internal Method
Тепловой	Номинальное значение	Единица измерения	Метод испытания
Температура плавления	245 to 249	°C	Internal Method
NOTE			
1.	when packed		

2.

100pcs chips

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

