

NatureFlex™ 90NM

Regenerated Cellulose

Innovia Films Ltd.

Описание материалов:

NatureFlex films are manufactured from renewable wood pulp harvested from plantations operating good forestry management principles. Heat-sealability and barrier properties are achieved through Innovia Films' proprietary coating technologies.

Literature reference: N500

1 side metallized, high barrier film for twistwrap

Главная Информация			
Характеристики	Барьерная смола Биоразлагаемый Compostable Содержание возобновляемых ресурсов		
Используется	Пленка Упаковка		
Формы	Пленка		
Пленки	Номинальное значение	Единица измерения	Метод испытания
Температура инициализации уплотнения ¹ (23 µm)	90.6 to 199	°C	
Скорость передачи кислорода (влажная) ² (24°C, 23 µm, 0.0% RH)	3.00	cm ³ /m ² /24 hr	ASTM F1927
Передача водяного пара ³	5.0	g/m ² /24 hr	ASTM E96
Датчик пленки	23.4	µm	Internal Method
Выход (23.4 µm)	29.9	m ² /kg	Internal Method
	104.14		
Оптимальная ширина декорации	144.78	cm	

NOTE	
1.	0.5s dwell, 10 psi
2.	RH: 0 to 5%
3.	100°F, 90%RH

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

