

ALKAMIX™ MB6009

Linear Low Density Polyethylene

Qenos Pty Ltd

Описание материалов:

ALKAMIX MB6009 is formulated with an antiblock additive at a concentration of 15 percent.

ALKAMIX MB6009 can be added to polythene during extrusion to reduce the blocking tendency of film, particularly where minimum blocking tendency is required. The level required may vary according to desired properties, however the recommended addition level is between 1 to 3 percent.

The maximum level of addition of ALKAMIX MB6009 based on both good manufacturing practice and to ensure conformance to the requirements to the United States Food and Drug Administration Regulations CFR21 is 6.5 percent, when added to a polyethylene formulation free of any antiblock additives.

Главная Информация			
Добавка	Антиблок (15%)		
Характеристики	Антиблокировка		
Используется	Смешивание		
Формы	Гранулы		
Физический	Номинальное значение	Единица измерения	Метод испытания
Плотность	0.980	g/cm ³	ASTM D1505

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай



WeChat