

BCC Resins BC 5009

Епоху; Epoxide

BCC Products Inc.

Описание материалов:

BC5009 is a very low viscosity, modified, unfilled, room temperature curing, general purpose resin system.

BC5009 is a clear-amber epoxy adhesive especially formulated for the bonding of wood and urethane model board. It may be also used as a laminating resin. The resin is color indicated (green) and will turn to a clear amber color as the hardener is mixed into the resin. This indicator system promotes fast and efficient mixing of the resin and hardener, insuring that they are thoroughly mixed yet wasting no time over mixing.

Главная Информация

Характеристики	Низкая вязкость Универсальный
Используется	Ламинат Универсальный Склеивание
Внешний вид	Прозрачный янтарь
Формы	Жидкость
Метод обработки	Ламинирование

Твердость	Номинальное значение	Метод испытания
Твердость дюрометра (Shore D, 24°C)	80	ASTM D2240

Тепловой	Номинальное значение	Единица измерения	Метод испытания
Температура отклонения при нагрузке (1.8 МПа, Unannealed)	71.1	°C	ASTM D648

Термокомплект	Номинальное значение	Единица измерения	Метод испытания
Компоненты термокомплекта			
Resin	Mixing ratio by weight: 25		
Hardening method	Mixing ratio by weight: 100		
Срок службы горшка (24°C)	30	min	
Терморегулирующая вязкость ¹ (24°C)	2100	cP	ASTM D2393
Время доставки (24°C)	16 - 24	hr	

Дополнительная информация

Use Procedure

Mix the resin and hardener in the ratio of 100 parts resin to 25 parts hardener, by weight. Continue mixing until the green indicator color disappears. The pot-life of a 125 gram mass will be approximately 30 minutes. When applied in a thin adhesive film, the best procedure is to allow overnight for full cure, however in some rigid structures the adhesive should be cured enough to handle in 6-8 hours.

NOTE

1. Brookfield

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

