

Algoflon® F 5

Polytetrafluoroethylene

Solvay Specialty Polymers

Описание материалов:

Algoflon® F 5 is a fine cut homopolymer PTFE powder that is white, granular and non-free flowing. It is designed for filled grades and in particular is recommended for compounds with glass fiber since it allows good degassing during the sintering process.

Main features of Algoflon® F 5 are:

Fine particle size

Narrow particle size distribution

Good blendability

Low porosity

Главная Информация			
Характеристики	Хорошая химическая стойкость		
Используется	Смешивание Добавка		
Рейтинг агентства	Управление по санитарному надзору за качеством пищевых продуктов и медикаментов 21 CFR 177,155		
Внешний вид	Белый		
Формы	Порошок		
Физический	Номинальное значение	Единица измерения	Метод испытания
Удельный вес	2.17		ASTM D792
Средний размер частиц	15	µm	Internal method
Сжатие-Радиальная	3.0	%	ASTM D4894
Плотность объема	380	g/l	ASTM D4894
Удлинение при разрыве	350	%	
Прочность на растяжение	40.0	MPa	ASTM D4894
Дополнительная информация			

Processing

Algoflon® F 5 is used for preparing filled products based on PTFE resins. Prior to use, Algoflon® F 5 powder needs to be conditioned above 19°C/66°F.

In order to obtain fully homogeneous compounds, it is necessary to mix Algoflon® F 5 and filler with high shear systems. Temperature must also be controlled (it should not rise above 40°C/104°F) during the mixing process to avoid agglomeration of PTFE and generation of white spots.

Algoflon® F 5 based compounds are processed using normal compression molding as similar to virgin fine cut PTFE.

Storage and Handling

Algoflon® PTFE fine cut powders must be stored and handled carefully to achieve defect free compounds and items. Temperatures that are too high should be avoided to prevent powder lumping and poor flow.

Storage and handling facilities should be clean since even very small foreign particles can cause defects in finished products. Keep resin drums closed and clean. Good housekeeping and careful handling are essential.

Safety and Toxicology

Before using Algoflon® PTFE fine cut powders, consult the product Material Safety Data Sheet and follow all label directions and handling precautions.

As with all PTFE materials, handling and processing should only be carried out in well ventilated areas. Vapor extractor units should be installed above processing equipment. Fumes must not be inhaled and eye and skin contact ought to be avoided. In case of skin contact wash with soap and water. In case of eye contact flush with water immediately and seek medical help.

Do not smoke in areas contaminated with powder, vapor or fumes.

See Material Safety Data Sheet for detailed advice on waste disposal methods.

Packaging

Algoflon® F 5 is packaged in 25 kg nonreturnable drums. Each drum has two bag liners made of polyethylene resin.

Additional Technical Information

For Material Safety Data Sheet or additional technical information consult your Solvay sales representative or the website:

www.solvayspecialtypolymers.com

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

СВЯЖИТЕСЬ С НАМИ

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

