

## FM® 680-1

Thermoset Polyimide

Cytec Industries Inc.

### Описание материалов:

FM® 680-1 polyimide adhesive is a non-metallic version of FM 680 film adhesive designed for continuous service at temperature up to 700°F (371°C). FM 680-1 adhesive was specifically developed for radar transparent applications requiring extreme environmental durability. FM 680-1 adhesive is capable of bonding composite laminates and a wide variety of high temperature metallic substrates such as stainless steel and titanium while maintaining thermal oxidative stability. FM 680-1 adhesive is an excellent candidate for aircraft engine applications or for the bonding of new composite materials requiring co-cure or consolidation temperature up to 735°F (391°C). This adhesive is processible under standard manufacturing operations at temperatures as low as 600°F (316°C) and can handle freestanding post-cure up to 735°F (391°C). To achieve maximum performance in bonding prepared metallic details the use of BR® 680 primer is recommended. FM 680-1 adhesive is a non-aluminum-filled, condensation polyimide supported on fiberglass cloth. It is available in film, foam and paste forms. FM 680-1 adhesive utilizes the NR-150 B2 chemistry developed by DuPont.

#### Suggested Applications:

Titanium bonding

Stainless steel bonding

Polyimide composite bonding

### Главная Информация

Характеристики	Хорошая адгезия Хорошая термическая стабильность Высокая термостойкость
Используется	Клей Аэрокосмическое применение Склейивание Пена
Внешний вид	Коричневый
Формы	Пленка Паста

Механические	Номинальное значение	Единица измерения
Прочность сдвига <sup>1</sup>		
24°C	20.8	MPa
177°C	19.3	MPa

### NOTE

FM 680-1 film adhesive, 0.10 psf  
(490 gsm), 6Al-4V Titanium 0.05  
in. (1.27 mm), Post-cure 16 hours  
at 600°F (316°C)

\* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

## Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

