

Sumiliteresin® PR-F-63 I

Phenolic

SBHPP

Описание материалов:

SUMILITERESIN® PR-F-63 I is a straight novolak phenolic resin. It is generally apply for foundry.

Characteristics

SUMILITERESIN® PR-F-63 I is a flake phenolic resin with good properties in foundry manufacture. It is designed in low molecule number and short gel time in order to get short process time or fast cure and high strength . It is preferable add hexamine about 15%/resin when applied in resin coated sand (RCS).

Главная Информация		
Характеристики	Высокая прочность	
	Ускоренная Настройка	
	Точка быстрого затвердевания	
Внешний вид	Желтый	
Формы	Шелковистый	
Физический	Номинальное значение	Единица измерения
Длина потока (125°C)	4.00 - 6.50	cm
Тепловой	Номинальное значение	Единица измерения
Температура плавления	79.0 - 89.0	°C
Uncured Properties	Номинальное значение	Единица измерения
Gel Time (150°C)	0.95 - 1.4	min

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай



WeChat