

## Zetpol® 4320

Acrylonitrile Butadiene Rubber

Zeon Corporation

### Описание материалов:

Hydrogenated NBR (HNBR) features high strength as well as resistance to heat, sour gasoline, and ozone. The low-temperature resistance grade provides outstanding physical properties across a wide range of temperatures, from -40 to 150°C. In terms of fuel-related applications, compared to rubber containing fluorine, Zetpol exhibits surpassed cost performance, while at the same time complying with the specific requirements of those applications. It also offers superior resistance to various lubricating oil additives. The use of Zetpol enables the manufacture of rubber parts including seals, hoses, and gaskets with excellent functionality at high temperatures, as it facilitates the design of high modulus compounds and maintains significant strength at high temperatures. Zetpol is also the ideal choice for oil drilling applications, because of its resistance capability to steam and acid, as well as crude oil and natural gas. In addition, Zetpol works well if applied to industrial equipment, since it readily adheres to various types of metal and exhibits excellent abrasion and chemical resistance. Furthermore, for various belts, such as synchronous belts and V-belts, Zetpol's premier dynamic characteristics, high strength, ozone resistance, and heat resistance contribute significantly to improving durability.

### Characteristics and applications

Improved low temperature TR10 of -37°C providing good heat and oil resistance. Very good for arctic oil and gas drilling applications as well as automotive uses. Suitable for sulfur and peroxide curing.

### Главная Информация

Характеристики	Кислотоупорный
	Сопротивление бензину
	Хорошая стойкость к истиранию
	Хорошая химическая стойкость
	Высокая термостойкость
	Высокая прочность
	Низкая термостойкость
	Маслостойкий
	Устойчивость к озону
Устойчивость к пару	

Используется	Автомобильные Приложения
	Применение нефти/газа

Физический	Номинальное значение	Единица измерения
Удельный вес	0.978	g/cm <sup>3</sup>
Вязкость Mooney	60	MU
Bound Acrylonitrile	19	%
Значение йода	27.0	mg/100 mg

\* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

## Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

