

Shin-Etsu Elastomer KE-2090-20A/B

Silicone Rubber, HTV

Shin-Etsu Silicones of America

Описание материалов:

Shin-Etsu KE-2090-20 is a selective self-adhesive liquid injection molding silicone. It is supplied as two components which are mixed in a 1:1 ratio to ensure easy and accurate blending. The viscosity of KE-2090-20 is low enough to allow easy pumping through most injection molding systems.

| Главная Информация | | |
|----------------------------------|--|-------------------|
| Характеристики | Низкая вязкость Обрабатываемость, хорошая | |
| Метод обработки | Литье под давлением (LIM) | |
| Физический | Номинальное значение | Единица измерения |
| Удельный вес | 1.07 | g/cm ³ |
| Твердость | Номинальное значение | Единица измерения |
| Твердость дюрометра | 21 | |
| Эластомеры | Номинальное значение | Единица измерения |
| Прочность на растяжение | 7.24 | MPa |
| Удлинение при растяжении (Break) | 970 | % |
| Tear Strength ¹ | 6.13 | kN/m |
| Термокомплект | Номинальное значение | Единица измерения |
| Срок годности (32°C) | 26 | wk |
| Дополнительная информация | | |
| Press / Post Cure: Press | | |
| Uncured Properties | Номинальное значение | Единица измерения |
| Время отверждения | 0.25 | hr |
| NOTE | | |
| 1. | B mould | |

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

