

SUPRENE® 501A

Ethylene Propylene Diene Terpolymer

SK Global Chemical

Описание материалов:

SUPRENE EPDM 501A is a low Mooney Viscosity and ENB type grade. It shows excellent mill processability. It has good flow and is suitable for molding complicated shaped products. It is also suitable for extrusion of cable.

Main uses of SUPRENE EPDM 501A are found in gasket, roll, electric parts, various rubber coated fabrics and general industrial parts.

| Главная Информация | |
|--------------------|--|
| Характеристики | Хороший поток Хорошая технологичность Низкая вязкость |
| Используется | Электрические детали Тканевые покрытия Прокладки Промышленные детали Применение проводов и кабелей |
| Формы | Тюк |
| Метод обработки | Экструзия Литье под давлением |

| Физический | Номинальное значение | Единица измерения | Метод испытания |
|---------------------------------------|----------------------|-------------------|-----------------|
| Удельный вес | 0.860 | g/cm ³ | ASTM D792 |
| Вязкость Mooney (ML 1+4, 100°C) | 46 | MU | ASTM D1646 |
| Ethylene Content | 53.0 | wt% | ASTM D3900 |
| Содержание этилидена норборнена (ENB) | 4.1 | wt% | ASTM D6047 |
| Содержание золы | 0.0100 | wt% | ASTM D5667 |
| Летучее вещество | 0.20 | wt% | ASTM D5668 |

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

