

Sumiliteresin® PR-F-47 I

Phenolic

SBHPP

Описание материалов:

SUMILITERESIN® PR-F-47 I is a bis-phenol-A modified novolak phenolic resin. It is generally apply for Foundry.

Characteristics

SUMILITERESIN® PR-F-47 I is flake phenolic resin with good properties in foundry manufacture. It is designed in low molecule number and modified with bis-phenol-A in order to get high strength and low thermal expansion. It is preferable add hexamine about 15%/resin when applied in resin coated sand (RCS).

Главная Информация		
Характеристики	Высокая прочность	
Внешний вид	Коричневый	
	Желтый	
Формы	Шелковистый	
Физический	Номинальное значение	Единица измерения
Длина потока (125°C)	100 - 136	mm
Тепловой	Номинальное значение	Единица измерения
Температура плавления	66.0 - 80.0	°C
Uncured Properties	Номинальное значение	Единица измерения
Gel Time (150°C)	1.9 - 2.4	min

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай



WeChat