

ELASTOSIL® R 401/40

Silicone

Wacker Chemie AG

Описание материалов:

Silicone Rubber, HTV
Exhaust-Pipe Suspensions, Automotive & Transportation
Architectural Textiles, Technical Textiles
Tents, Technical Textiles
Coating of Fabrics and Textiles, Technical Textiles
Vibration Dampers, Automotive & Transportation
Molded Parts, Food Contact, Plastics and Rubber Processing
Molded Parts, Automotive, Plastics and Rubber Processing
Molded Seals, Plastics and Rubber Processing
Molded Parts, Technical, Plastics and Rubber Processing
Extrudates, Automotive, Plastics and Rubber Processing
Extrudates, food contact, Plastics and Rubber Processing
Extruded parts; tap water and wastewater contact, Plastics and Rubber Processing
Molded parts; tap water and wastewater contact, Plastics and Rubber Processing
Extrudates, Technical, Plastics and Rubber Processing
Membranes, Automotive & Transportation
Sealant Profiles, Construction

Главная Информация			
UL YellowCard	E75704-101818639		
Характеристики	Приемлемый пищевой контакт		
	Общее назначение		
Используется	Автомобильные Приложения		
	Уплотнение		
	Прокладки		
	Применение питьевой воды		
	Профили		
	Уплотнения		
	Клапаны/Детали Клапана		
Метод обработки	Применение проводов и кабелей		
	Каландрирование		
	Прессформа сжатия		
	Экструзия		
	Пресс-форма		
	Экструзионный профиль		
Uncured Properties	Номинальное значение	Единица измерения	Метод испытания

Цвет	Clear/Transparent		
Плотность	1.12	g/cm ³	ISO 1183
Cured Properties	Номинальное значение	Единица измерения	Метод испытания
Твердость по суше (Shore A)	42		DIN 53505
Прочность на растяжение	10.0	MPa	DIN 53504
Удлинение при разрыве	580	%	DIN 53504
Комплект сжатия	36	%	DIN ISO 815-B
Tear Strength	23.0	kN/m	ASTM D624B
Восстановленная устойчивость	53	%	DIN 53512

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

