

ELASTOSIL® A 07

Silicone

Wacker Chemie AG

Описание материалов:

Silicone Rubber, RTV-1

Bonding & Sealing, Mechanical and Plant Engineering

Bonding & Sealing, Lighting

Bonding & Sealing, Adhesives and Sealants

Bonding & Sealing, Household Appliances

Bonding & Sealing, Renewable Energies

Small Appliances, Household Appliances

Heating and Air Conditioning, Household Appliances

Heating and Air Conditioning, Mechanical and Plant Engineering

Главная Информация

Используется	Клеи
	Склеивание
	Герметики

Uncured Properties	Номинальное значение	Единица измерения	Метод испытания
Цвет	Colorless		
Плотность			
--	0.980	g/cm ³	DIN 51757
--	1.02	g/cm ³	ISO 2781
Вязкость	8.0	Pa·s	
Время отверждения	12	hr	
Skin Forming Time ¹ (23°C)	3.0	min	

Cured Properties	Номинальное значение	Единица измерения	Метод испытания
Твердость по суше (Shore A)	20		ISO 868
Прочность на растяжение	1.50	MPa	ISO 37
Удлинение при разрыве	300	%	ISO 37
Tear Strength	4.00	kN/m	ASTM D624B

NOTE

1.	50% R.H
----	---------

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.
Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

