SUSHENG
Import & Export Trading CO.,LTD.
www.russianpolymer.com Email: sales@su-jiao.com

Escor™ 5000

Ethylene Acrylic Acid Copolymer Resin

ExxonMobil Chemical

Описание материалов:

Escor 5000 is mainly used for extrusion coating, coextrusion coating and extrusion compounding. It can be well bonded to polar substrates, aluminum foils, metal films, paper, steel and glass surfaces. Provides an excellent balance of adhesion to the surface of the substrate and interlayer adhesion to coextruded low density polyethylene and ethylene vinyl acetate. Excellent adhesive polymer in film.

Главная Информация

Физический	Номинальное значение	Единица измерения	Метод испытания
Массовый расход расплава (MFR) (190°C/2.16 kg)	8.2	g/10 min	ASTM D1238
Содержание акриловой кислоты	6.0	wt%	ExxonMobil Method

Юридическое заявление

有关潜在食品接触应用合规信息(例如:FDA,EU,HPFB),请与埃克森美孚化工客户服务代表联系.本产品不宜在医疗应用中使用,亦不应在任何此类应用中使用

Инструкции по экструзии

Excellent results are obtained in extrusion coating at 260°C - 280°C (500°F - 536°F) temperature range. Processing temperatures above 300°C (572°F) may cause resin degradation. To minimize corrosion risk, all exposed metal surfaces in the extruder and die should be made from corrosion resistant metals or nickel/chrome plated. ESCOR should be fed into the extruder after LDPE of a similar or higher melt index. Machines should always be completely purged with LDPE or a suitable cleaning compound before shutdown.

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

WeChat

Page 1