

Selvol™ ULTALUX FP

Polyvinyl Alcohol

Sekisui Chemical Company, Ltd.

Описание материалов:

SELVOL™ ULTALUX FP polyvinyl alcohol (PVOH) finds application in skin care masks and eye shadow, eye liners, mascara, and other color cosmetics applications. It is also ideal for instant lifts and other anti-aging formulations. The low solution viscosity of SELVOL™ ULTALUX FP makes it ideal for use in BB creams and other applications where multiple functions are required. Used in personal care formulations for decades, SELVOL™ ULTALUX FP is a cosmetic grade tested for high quality and purity and is non-irritating on skin in skin care formulations as verified by third party testing.

Главная Информация

Используется	Косметика	
Физический	Номинальное значение	Единица измерения
РН-4% водного раствора	4.5 to 6.5	
Вязкость раствора-15% водного раствора при 20 °C	270 to 310	mPa·s
Adhesion to Glass	80 to 120	g
Механические	Номинальное значение	Единица измерения
Модуль растяжения ¹	17.2 to 24.1	MPa
Прочность на растяжение ²	2.07 to 4.14	MPa
Удлинение при растяжении ³ (Break)	50 to 70	%

NOTE

Tensile properties and adhesion were measured on films containing 12% PVOH and 3% glycerin after casting and drying in a controlled temperature and humidity room for 24 hours

1.

Tensile properties and adhesion were measured on films containing 12% PVOH and 3% glycerin after casting and drying in a controlled temperature and humidity room for 24 hours

2.

Tensile properties and adhesion were measured on films containing 12% PVOH and 3% glycerin after casting and drying in a controlled temperature and humidity room for 24 hours

3.

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжоу

Район Фэнсянь, Шанхай, Китай

