

## PEARLSTICK® 45-60/25

Thermoplastic Polyurethane Elastomer (Polycaprolactone)

Lubrizol Advanced Materials, Inc.

### Описание материалов:

Pearlstick® 45-60/25 is an elastic, linear, aromatic polyurethane, supplied in form of white spherical granules with an extremely high crystallisation speed and a low thermoplasticity level.

#### APPLICATIONS:

Pearlstick® 45-60/25 is used for the production of adhesives for bonding plasticized PVC to plasticized PVC or other materials such as leather, textiles, rubber, in the shoe industry. The adhesives based on Pearlstick® 45-60/25 show:

High green strength values.

Easier heat activation (wide range of activation temperatures).

Long and high hot-tack (tack retention).

Pearlstick® 45-60/25 may be suitable as a raw material for the production of one-component adhesives.

Главная Информация			
Характеристики	Ароматические Сопротивление гидролизу		
Используется	Клей		
Внешний вид	Белый		
Формы	Частицы		
Физический	Номинальное значение	Единица измерения	Метод испытания
Плотность (20°C)	1.19	g/cm <sup>3</sup>	ISO 2781
Вязкость <sup>1</sup> (20°C)	2.30 - 2.70	Pa·s	Internal method
Гидростатическое сопротивление	Good		Internal method
Hydroxyl Value	0.10	%	Internal method
Температура активации	50	°C	EN 12961

Дополнительная информация	Номинальное значение	Единица измерения	Метод испытания
SOLUBILITY: Pearlstick® 45-60/25 is soluble in Acetone, Methyl Ethyl Ketone (MEK), Cyclohexanone, Dimethyl formamide, (DMF), Tetrahydrofuran (THF). Diluting solvents such as Toluene and Ethyl Acetate can be added. The solvents and diluents should be water-free (max. 0.1%), so as to avoid subsequent side reactions during crosslinking with isocyanate. Pearlstick® 45-60/25 should be dissolved in closed tanks and the use of high shear equipments is advisable. The final viscosity figures can vary, depending on the stirring process and on the solvent/diluents ratios.			

### NOTE

1. Brookfield RVF sp.5, 20 rpm solution at 15% in MEK

\* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

**Susheng Import & Export Trading Co.,Ltd.**

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

