

CALIBRE™ 340 TNIR

Polycarbonate Resin

Trinseo

Описание материалов:

CALIBRE™ 340 TNIR Polycarbonate Resin provides transparent solar heat reduction to solid or multi-wall sheets via the co-extrusion of a 150 to 250 µm thick layer in between the bulk PC layer and the UV cap layer. It is recommended to use CALIBRE 320UV as UV cap layer.

Main Characteristics:

Transparent

Solar Heat Reduction

Neutral Tint

High Light Transmission

Applications

Clear sheet extrusion

Solid and Multi Wall Polycarbonate sheet

Главная Информация			
Характеристики	Высокая светопередача		
Используется	Лист		
Внешний вид	Прозрачный/прозрачный		
Формы	Гранулы		
Физический	Номинальное значение	Единица измерения	Метод испытания
Плотность	1.20	g/cm ³	ISO 1183
Массовый расход расплава (MFR) (300°C/1.2 kg)	8.0	g/10 min	ISO 1133
Оптический	Номинальное значение	Единица измерения	Метод испытания
Коэффициент пропускания			Internal Method
-- 1	60.0	%	
-- 2	67.0	%	
Дополнительная информация	Номинальное значение	Единица измерения	Метод испытания
Уменьшение солнечного тепла			Internal Method
-- 3	10 to 11	°C	
-- 4	10 to 11	°C	
NOTE			

Light transmission with a 200 µm thick co-extruded layer in between the bulk PC layer (CALIBRE 503-5 TC 030003) and a 40 µm UV cap layer (CALIBRE 320UV) for a 10 mm thick twin wall polycarbonate sheet.

1.

2. Light transmission with a 200 µm thick co-extruded layer in between the bulk PC layer (CALIBRE 302-5 TC 030003) and a 40 µm UV cap layer (CALIBRE 320UV) for a 2 mm thick solid polycarbonate sheet.

3. Solar Heat Reduction with a 200 1m thick co-extruded layer in between the bulk PC layer (CALIBRE 503-5 TC 030003) and a 40 1m UV cap layer (CALIBRE 320UV) for a 10 mm thick twin wall polycarbonate sheet.

4. Solar Heat Reduction with a 200 1m thick co-extruded layer in between the bulk PC layer (CALIBRE 302-5 TC 030003) and a 40 1m UV cap layer (CALIBRE 320UV) for a 2 mm thick solid polycarbonate sheet.

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

