

POLYCASA® CAST Argenta

Polymethyl Methacrylate Acrylic

Polycasa

Описание материалов:

CAST Argenta is the brand name for cast polymethylmethacrylate sheets from Polycasa® , with special visual characteristics.

CAST Argenta sheets are as easy to handle as standard Polycasa CAST material. Fabricating and finishing techniques such as sawing, drilling, printing, milling, mechanical polishing, thermoforming, hot bending and laser cutting (on coloured surface) do not offer any problems to this special product.

CHARACTERISTICS

Unique sparkling look, creating an intriguing depth effect.

Two surfaces: a sparkling colour surface with a fascinating gloss and deepness effect, and a metallic silver surface with opaque appearance.

Material is almost opaque in flat application, but can be easily thermoformed to any shape, thus gaining light transmission to 30-50%.

Due to inner composition and production process, material has a certain particle orientation. This results in a colour which has different colour shades.

The colour intensity of the thermoformed piece reduces/ varies depending on the thermoformed shape.

APPLICATIONS

Luxury POP displays.

High-end shop interior design.

Interior design (restaurants, casinos, museums, flag ship stores).

Exhibitions.

Furniture.

Advertising.

Lighting applications.

Thermoformed pieces (caravan interiors, yacht furniture).

Главная Информация

Характеристики	Кислотоупорный Щелочестойкие Глянцевый Низкое поглощение воды Маслостойкий Соленая вода/спрей		
Используется	Декоративные дисплеи Дисплеи Мебель Применение освещения Применение термоформования		
Внешний вид	Доступные цвета Глянцевая отделка Непрозрачный		
Формы	Лист		
Воздействие	Номинальное значение	Единица измерения	Метод испытания

Charpy Unnotched Impact Strength	12	kJ/m ²	ISO 179
Тепловой	Номинальное значение	Единица измерения	Метод испытания
Викат Температура размягчения	110	°C	ISO 306/A50
Максимальная температура обслуживания			
continuous use	80	°C	
short term use	90	°C	
Light Transmission			DIN 13468
--	< 5.0	%	
After thermoforming	< 50	%	
Температура-Термоформовка	130 to 190	°C	

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

