

Aquivion® D83-06A

Perfluorosulfonic Acid

Solvay Specialty Polymers

Описание материалов:

Aquivion® D83-06A is a perfluorosulfonic acid (PFSA) ionomer dispersion that exhibits an Equivalent Weight (EW) of 830 g/eq. Polymer concentration is 6% percent. Solvent system is 20% water, 40% 1-propanol, and 40% 2-propanol.

Aquivion® PFSA dispersions are based on the unique Short Side Chain copolymer of Tetrafluoroethylene (TFE) and Sulfonyl Fluoride Vinyl Ether (SFVE) F2C=CF-O-CF2CF2-SO2F produced by Solvay. The PFSA ionomer dispersions contain its acid form (-SO3H) and are available in various solvent systems, EWs and concentrations.

These dispersions can be used to produce PEM fuel cell electrodes and electrochemical cell electrodes, to manufacture or repair ion exchange membranes, to produce super-acid catalysts, and for the surface treatment of PTFE membranes to improve wetting behavior.

Главная Информация			
Физический	Номинальное значение	Единица измерения	Метод испытания
HSE/классификация перевозки	Flammable		
Эквивалент (EW) ¹	810 - 850	g/eq	Internal method
Концентрация полимера	6	%	TGA
Плотность (25°C)	875	kg/m ³	Internal method
Содержание растворителя в воде	25	%	
Система растворителя	20% water, 40% 1-propanol, 40% 2-propanol		
Вязкость ² (25°C)	80 - 100	mPa·s	ASTM D2196
Общее содержание кислоты	1.17 - 1.23	meq/g	Internal method
Воспламеняемость-В условиях окружающей среды	Yes		

Дополнительная информация

HEALTH, SAFETY AND ENVIRONMENT

Aquivion® PFSA dispersions are not harmful if used and handled according to standard processing procedures (see for example the "Guide to the Safe Handling of Fluoropolymer Resins" issued by the Society of the Plastics Industry). If handled inappropriately (e.g. overheating above 230°C for extended period of time) the dispersions may release harmful toxic chemicals. By their chemical properties Aquivion® PFSA dispersion grades are classified as hazardous material subject to transportation regulations (ADR, IATA, IMDG). D83-06A is flammable whereas D83-24B and D79-20BS are corrosive (R-SO3H being a strong acid, measured pH < 2). Please refer to corresponding Material Safety Data Sheets for more information on handling and safety.

PACKAGING, SHIPMENT AND STORAGE

Aquivion® PFSA D83-06A and D83-24B are available in 0.5, 5 and 60 liter containers (D79-20BS: 0.25 liter). It is recommended to store the product at 25 °C (77 °F) in a clean temperature-controlled and well ventilated environment, protected from direct sunlight and other sources of heat or irradiation. Containers should be kept tightly closed to avoid solvent evaporation. D83-06A shall be kept away from sparks, flames or other possible source of ignition.

NOTE

- eq = mol SO3H
- Dynamic mechanical spectrometer rheometer RFS III geometry: Couette mode: steady speed scan test value: 40 1 / s

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

