

## Styropek® BF 495

Expanded Polystyrene

Styropek S.A. de C.V.

### Описание материалов:

Styropek® BF products can be used in a wide variety of applications including blocks for construction, panels, thermal and acoustical insulation, and general packaging. Additional applications include ICF's ("insulated concrete forms"), thin walled custom molding, lost foam and other general protective packaging.

Modified expandable polystyrene (EPS) / non-flammable / ant flame / auto-extinguishable that containing approximately 5.5 to 6.4 wt% pentane as blowing agent.

All products are supplied as spherical beads with a bulk density of approximately 40 lb/ft<sup>3</sup> (640 kg/m<sup>3</sup>).

Styropek® BF products are compatible with many anti-stat, mineral oil, color additives and other additives added during processing.

Styropek® BF products do not contain chlorofluorocarbons and hydrofluorocarbons compounds.

Intended uses

Shape molding applications with requirements of non-flammable material, thickness of wall >6 mm, excellent cycle time and surface appearance.

Blocks of high density with excellent surface appearance after cutting.

Главная Информация		
UL YellowCard	E474710-102172942	
Добавка	Пенообразователь (6) 3	
Характеристики	Перерабатываемые материалы	
	Пенопласт	
	Самопогасающийся	
	Огнестойкий	
Используется	Упаковка	
	Строительные материалы	
	Область архитектурного применения	
	Изоляционный материал	
	Пена	
Рейтинг агентства	ASTM C 578	
	ASTM E 84	
	EC 1907/2006 (REACH)	
Соответствие RoHS	Соответствие RoHS	
Формы	Сфера	
Физический	Номинальное значение	Единица измерения
Видимая плотность	0.64	g/cm <sup>3</sup>
Дополнительная информация	Номинальное значение	Единица измерения
Bead Size		
< 350.0 µm		%

350.0 to 850.0 $\mu\text{m}$	> 97	%
Расширенная плотность	18.0 - 40.0	kg/m <sup>3</sup>
Остатки мономера		ppm

\* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

## Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

