

## Styropek® BFL 295

Expanded Polystyrene

Styropek S.A. de C.V.

### Описание материалов:

Styropek® BFL products can be used in a wide variety of applications, including blocks for panels, general insulation, below grade use, fabrication, flotation, and general packaging.

Additional applications include ICF's ("insulated concrete forms"), thin or thick walled custom molding, and other general protective packaging.

Modified expandable polystyrene (EPS) / non-flammable / antifiame / auto-extinguishable containing approximately 3.45 - 3.65 wt% pentane as the blowing agent.

All products are supplied as spherical beads with a bulk density of approximately 40 lb/ft<sup>3</sup> (640 kg/m<sup>3</sup>).

Styropek® BFL products are compatible with many anti-stat, mineral oil and color additives that can be added during processing.

Styropek® BFL products do not contain chlorofluorocarbons and hydrofluorocarbons compounds.

Intended uses

Block molding applications, low and high densities requiring excellent fusion or with regrind.

Главная Информация		
UL YellowCard	E474710-102172942	
Добавка	Пенообразователь (от 3 до 4%) 3	
Характеристики	Перерабатываемые материалы	
	Пенопласт	
	Самопогасающийся	
	Огнестойкий	
Используется	Упаковка	
	Строительные материалы	
	Область архитектурного применения	
	Изоляционный материал	
	Пена	
Рейтинг агентства	ASTM C 578	
	ASTM E 84	
	EC 1907/2006 (REACH)	
Соответствие RoHS	Соответствие RoHS	
Формы	Сфера	
Физический	Номинальное значение	Единица измерения
Видимая плотность	0.64	g/cm <sup>3</sup>
Дополнительная информация	Номинальное значение	Единица измерения
Bead Size (0.850 to 1.70mm)	> 96	%
Расширенная плотность	15.0 - 110	kg/m <sup>3</sup>
Остатки мономера		ppm

\* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

## Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

