

Baytec® SPR-186A

Polyurethane (Polyether, MDI)

Covestro - PUR

Описание материалов:

Baytec SPR-186A is a two-component 100%-solids spray system with a Shore A hardness of 86. The isocyanate component is a modified diphenylmethane diisocyanate (MDI) quasi-prepolymer and the polyol component is a polyether blend. The system can be pigmented to most any color. As with any product, use of the Baytec SPR-186A in a given application must be tested (including field testing, etc.) in advance by the user to determine suitability.

Главная Информация			
Формы	Жидкость		
Метод обработки	Распыление		
Физический	Номинальное значение	Единица измерения	Метод испытания
Удельный вес	1.06	g/cm ³	ASTM D792
Твердость	Номинальное значение	Единица измерения	Метод испытания
Твердость дюрометра (Shore A)	86		ASTM D2240
Механические	Номинальное значение	Единица измерения	Метод испытания
Устойчивость к истиранию (1000 Cycles, 1000 g, H-18 Wheel)	405	mg	ASTM D1044
Эластомеры	Номинальное значение	Единица измерения	Метод испытания
Прочность на растяжение (Break)	11.6	MPa	ASTM D412
Удлинение при растяжении (Break)	120	%	ASTM D412
Tear Strength (Split)	11	kN/m	ASTM D1938
Термокомплект	Номинальное значение		
Компоненты термокомплекта			
Component a	Mixing ratio by weight: 65, mixing ratio by capacity: 60		
Component B	Mixing ratio by weight: 100, mixing ratio by capacity: 100		

Дополнительная информация	
Part A	
Type: Isocyanate	
Appearance: Clear amber liquid	
Specific Gravity @ 25°C: 1.1	
Viscosity @25°C: 1800 mPa	
Flash Point, PMCC: 210°C	
NCO: 12 wt%	
Part B	
Type: Polyol	
Appearance: Off white liquid	
Specific Gravity @ 25°C: 1.04	
Viscosity @25°C: 1800 mPa-s	
Flash Point, PMCC: 201°C	
Hydroxyl Number: 103 mg KOH/g	
Processing Temperature: 20 to 70°C Gel Time: 10 to 15 sec Tack-Free: 1 min	

* Отказ от ответственности: Информация на этой странице предоставлена производителем, и поставщик документа не несет никакой юридической ответственности. Все права защищены. Пожалуйста, немедленно свяжитесь с нами в случае каких-либо нарушений.

Свяжитесь с нами

Susheng Import & Export Trading Co.,Ltd.

Телефон: +86-021-58958519

Мобильный телефон: +86-13424755533

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

