# Geon™ Vinyl Flexible XV3772

Flexible Polyvinyl Chloride

PolyOne Corporation

## Описание материалов:

Geon™Vinyl Flexible XV3772 is a flexible polyvinyl chloride product. It can be processed by injection molding and is available in North America, Africa and the Middle East, Latin America, Europe or Asia Pacific. Geon™The application areas of Vinyl Flexible XV3772 include food contact applications and medical/health care. The main characteristics are: accessible food.

| Главная Информация | | | |
|---|---|---|---|
| Характеристики | Соответствие пищевого контакта | | |
| Используется | Медицинские принадлежности/принадлежности для ухода | | |
| Рейтинг агентства | FDA пищевой контакт, не Номинальный | | |
| Внешний вид | Прозрачный/прозрачный | | |
| Формы | Частицы | | |
| Метод обработки | Литье под давлением | | |
| **Физический** | **Номинальное значение** | **Единица измерения** | **Метод испытания** |
| Удельный вес | 1.20 | g/cm³ | ASTM D792 |
| **Твердость** | **Номинальное значение** | **Единица измерения** | **Метод испытания** |
| Твердость дюрометра (Shore A, 10 sec) | 70 | | ASTM D2240 |
| **Механические** | **Номинальное значение** | **Единица измерения** | **Метод испытания** |
| Прочность на растяжение [1] | | | ASTM D638 |
| Fracture | 15.9 | MPa | ASTM D638 |
| 100% strain | 7.24 | MPa | ASTM D638 |
| Удлинение при растяжении [2] (Break) | 450 | % | ASTM D638 |
| **Тепловой** | **Номинальное значение** | **Единица измерения** | **Метод испытания** |
| Температура ломкости | -32.2 | °C | ASTM D746 |

**Дополнительная информация**

□□:□□□□□□□□□□□□□□□□□□□□□□□□□□□□□□□□□□□□□□□□21□□□□.□□□□□□,□□□“□□□□□□□□□”.□□□□□□□□□□□□□□□□□□□

Email: sales@su-jiao.com

Адрес: Господин Чжао

Район Фэнсянь, Шанхай, Китай

WeChat